


# GLITTER



**FEED MATERIAL** into plotter/cutter so that the media faces up.




**PLACE MASK** over the graphic, making sure to smooth out any air bubbles.  
**Remove Backing -**



**PRINT DESIGN** in positive form.



**PREHEAT & POSITION-** Preheat garment for 10 seconds, prior to application. Position & place cover sheet over graphic.



**CUT DESIGN-** If cutting through ink, let the print dry for 2-4 hours, otherwise you may cut immediately. Dry times may vary.



**HEAT APPLY -** Temperature: 320°F; 160°C  
 Time: 15 seconds  
 Pressure: Medium #5 on a Hotronix® heat press.



**WEED** Away the excess media. If the design was cut immediately, the print must dry 30-60 minutes before proceeding.



**PEEL MASK COLD -**

## Description

For use with solvent, eco solvent or thermo-resin print and cut systems. CAD-COLOUR® Glitter is thicker than most digital media's. The translucent white material allows the glitter to assume the look of the logo. CAD-COLOUR® Glitter offers excellent opacity on all colours.

## Recommended Fabrics

100% cotton  
 100% polyester  
 Poly/cotton blends  
 Polyester knits  
 Polyester mesh  
 Poly/foam & cotton caps

*Due to the combination of fabrics, weaves, coatings and dyes used in the textile industry, Stahls' recommends and provides samples of our materials and media's for testing.*

## Accessories Required

CAD-COLOUR® Magic Mask Low Tack Cover Sheet  
 EZWeeder® or Tweezers

## Cutting Notes

Be sure to perform test cuts to ensure proper blade depth when cutting. Cutting too deep will result in weeding or masking difficulties.

## Care Instructions

For best results, turn garment inside out. Machine wash warm or cold using mild detergent. Do not bleach. Do not iron directly on transfer. Tumble dry low setting. Do not dry clean.

## Storage

If designs will not be heat applied immediately, return masked designs to paper backing for storage. Avoid humid spaces and extreme changes in temperature.

## HEAT APPLICATION

Temperature: 320°F; 160°C  
 Time: 15 Seconds  
 Pressure: Medium (#5)



## CUTTER GUIDELINES

CUTTER	BLADE	FORCE	OFFSET	SPEED
Roland VP-300	45°	120g	.25	30cm/s
Roland SP-300	45°	110g	.25	30cm/s

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.

CAD-CUT, CAD-COLOR, CAD-LAB, Solutions & Hotronix are trademarks & ® trademarks of Stahls' ID Direct™ with one or more patents or patents pending.

© Stahls' ID Direct™ 2009 - All International Rights Reserved